

Indicative material's picture:



Commercial name: Alaska Gold

Country of origin: India

Mineralogical type: Granite

Physico-mechanical properties - Indicative lab test results (*):

Apparent Density	~2,680 kg/m ³
Open Porosity	~0.25 - 0.35%
Water Absorption	~0.20%
Flexural Strength	~13 - 15 MPa
Compressive Strength	~160 - 180 MPa
Abrasion Resistance	~22 cm ³ /50 cm ²
Mohs Hardness	~6 to 7
Modulus of Rupture	~14 - 16 MPa
Thermal Expansion	~6.0 x 10 ⁻⁶ /°C

This information is based on our present knowledge out of laboratory tests and other information sources.. However, this shall not constitute a guarantee for any specific batch of stone, and shall not establish a legally valid contractual