


Indicative material's picture:



Commercial name: G664

Country of origin: China

Mineralogical type: Granite

Physico-mechanical properties - Indicative lab test results (*):

Apparent density ~2,610 kg/m³

Open porosity ~0.30 - 0.35%

Water absorption ~0.31%

Flexural strength ~12.8 MPa

Compressive strength ~128.5 MPa

Abrasion resistance ~23 cm³/50 cm²

Mohs Hardness ~6 to 7

Modulus of Rupture ~13 - 15 MPa

Thermal Expansion ~6-8 x 10⁻⁶ /°C

This information is based on our present knowledge out of laboratory tests and other information sources.. However, this shall not constitute a guarantee for any specific batch of stone, and shall not establish a legally valid contractual